

CLAIMS

1. An apparatus for the continuous wet granulation of a powder material, comprising:
  - 5 - a barrel having a granulation chamber provided between a first part (B) and a second part (B') of said barrel, the first part (B) being provided with at least one first inlet (1) connected with said granulation chamber for receiving said powder material and for supplying it to said granulation chamber and with at least one second inlet (2) connected  
10 with said granulation chamber for receiving a granulating liquid and for supplying it to said granulation chamber, said granulation chamber having an aperture (9) for discharge of granules from said barrel, and
  - at least one continuously operated transporting means (S) provided in  
15 said granulation chamber for advancing said powder material toward the end of said granulation chamber while granulating said powder material with the aid of said granulating liquid, each said transporting means (S) comprising at least a first transport zone (4) at its rear end, an agglomeration zone (5) downstream from the first transport zone (4), and a second transport zone (8) at its front end, said at least one  
20 first inlet (1) and said at least one second inlet (2) of the barrel being positioned above the at least one first transport zone (4) of each said at least one transporting means (S),  
wherein said aperture (9) has a shape tightly fitting the terminal portion of said at least one transporting means (S) for directly discharging said  
25 granules from the granulation chamber without developing a pressure gradient at the exit of the granulation chamber.
2. An apparatus according to claim 1, characterised in that each said at least  
30 one transporting means (S) further comprises one or more additional transport zones (6, 8) and one or more additional agglomeration zones (7), each agglomeration zone (5, 7) being positioned between two transport zones (4, 6, 8).

RECEIVED BY  
ART 34 ANDT

3. An apparatus according to claim 1 or claim 2, characterised in that said transporting means (S) is a rotating transporting means.
4. An apparatus according to any of claims 1 to 3, characterised in that said  
5 transporting means (S) is a single screw.
5. An apparatus according to any of claims 1 to 3, characterised in that said transporting means (S) is a twin screw.
- 10 6. An apparatus according to claim 4 or claim 5, characterised in that the length to diameter ratio of each screw is within a range from about 15 to about 60.
- 15 7. An apparatus according to any of claims 1 to 6, characterised in that the cumulative lengths of the agglomeration zones (5, 7) represent from about 8% to about 30% of the length of the transporting means (S).
- 20 8. An apparatus according to any of claims 1 to 7, characterised in that the cumulative lengths of the agglomeration zones (5, 7) represent from about 10% to about 25% of the length of the transporting means (S).
- 25 9. An apparatus according to any of claims 1 to 8, characterised in that the respective dimensions of the first inlet (1) for receiving the powder material and of the second inlet (2) for receiving the granulation liquid are such that the weight ratio of the granulating liquid to the powder material is not above 16:100.
- 30 10. An apparatus according to any of claims 1 to 9, characterised in that the respective dimensions of the first inlet (1) for receiving the powder material and of the second inlet (2) for receiving the granulation liquid are such that the weight ratio of the granulating liquid to the powder material is not above 12:100.

11. An apparatus according to any of claims 1 to 10, characterised in that the respective dimensions of the first inlet (1) for receiving the powder material and of the second inlet (2) for receiving the granulation liquid are such that the weight ratio of the granulating liquid to the powder material is not  
5 above 8:100.
12. An apparatus according to any of claims 1 to 11, characterised in that the respective dimensions of the first inlet (1) for receiving the powder material and of the second inlet (2) for receiving the granulation liquid are such that  
10 the weight ratio of the granulating liquid to the powder material is not below 2:100.
13. An apparatus according to any of claims 1 to 12, characterised in that the respective dimensions of the first inlet (1) for receiving the powder material and of the second inlet (2) for receiving the granulation liquid are such that  
15 the weight ratio of the granulating liquid to the powder material is not below 4:100.
14. A process for the continuous wet granulation of a powder material,  
20 comprising continuously operating an apparatus according to any of claims 1 to 13.
15. A process for the continuous wet granulation of a powder material, comprising the steps of :  
25 (a) feeding a powder material to a first transport zone (4) of a transporting means,  
(b) feeding a granulating liquid to said first transport zone (4) of said transporting means,  
(c) transporting said powder material and said granulating liquid from said  
30 first transport zone (4) to an agglomeration zone (5) of said transporting means downstream of said first transport zone (4) for agglomerating said wet powder material,

EP 1 479 797  
147 979 797

- (d) transporting said agglomerated material from said agglomeration zone (5) to a second transport zone (8) of said transporting means downstream of said agglomeration zone (5) for producing granules, and
- 5 (e) directly discharging said granules from said second transport zone (8) of said transporting means without submitting said granules to any pressure gradient.
- 10 16. A continuous wet granulation process according to claim 15, further comprising the step of transporting said agglomerated material from said agglomeration zone (5) to said second transport zone (8) of said transporting means through one or more combinations of an additional intermediate transport zone (6) followed by an additional intermediate agglomeration zone (7).
- 15 17. A continuous wet granulation process according to claim 15 or claim 16, characterised in that said transporting means is a rotating transporting means.
- 20 18. A continuous wet granulation process according to any of claims 15 to 17, characterised in that said transporting means is a single screw.
19. A continuous wet granulation process according to any of claims 15 to 17, characterised in that said transporting means is a twin screw.
- 25 20. A continuous wet granulation process according to any of claims 15 to 19, characterised in that the residence time of said powder material in said transporting means is in the range of about 5 seconds to about 180 seconds.
- 30 21. A continuous wet granulation process according to any of claims 15 to 20, characterised in that the residence time of said powder material in said

transporting means is in the range of about 20 seconds to about 60 seconds.

22. A continuous wet granulation process according to any of claims 15 to 21,  
5 characterised in that said powder material contains a biologically-active ingredient.

23. A continuous wet granulation process according to claim 22, characterised  
10 in that the content of said biologically-active ingredient in powder material is within a range from 0.1% by weight to 99% by weight.

24. A continuous wet granulation process according to claim 22 or claim 23,  
characterised in that said biologically-active ingredient is a poorly soluble  
15 drug belonging to Class II or Class IV of the Biopharmaceutical Classification System.

25. A continuous wet granulation process according to any of claims 15 to 21,  
characterised in that said powder material is selected from foodstuffs,  
catalysts, chemicals, fertilisers, detergents and mineral ores.  
20

26. A continuous wet granulation process according to any of claims 15 to 25,  
characterised in that the amount of the said granulating liquid is from about  
2% to about 16% by weight of the powder material.

25 27. A continuous wet granulation process according to any of claims 15 to 26,  
characterised in that the amount of the said granulating liquid is from about  
4% to about 12% by weight of the powder material.

28. A continuous wet granulation process according to any of claims 15 to 27,  
30 being carried out at a temperature within a range from about 10°C to about  
50°C.

29. A continuous wet granulation process according to any of claims 15 to 28, characterised in further comprising a granule drying step (f) subsequent to discharging step (e).
- 5 30. A continuous wet granulation process according to any of claims 15 to 29, characterised in further comprising a granule dry milling step subsequent to discharging step (e).
- 10 31. A continuous wet granulation process according to any of claims 22 to 24, characterised in that said powder material further contains one or more physiologically acceptable excipients.
- 15 32. A granule population obtainable by operating an apparatus according to any of claims 1 to 13 or by performing a process according to any of claims 14 to 31.
33. A granule population according to claim 32, having an average size within a range from about 250  $\mu\text{m}$  to about 1,000  $\mu\text{m}$ .
- 20 34. A granule population according to claim 32 or claim 33, having an average size within a range from about 250  $\mu\text{m}$  to about 700  $\mu\text{m}$ .
35. A solid shaped article obtainable from a granule population according to any of claims 32 to 34.
- 25 36. A solid shaped article according to claim 35, in the form of a tablet, a composite article or a capsule.
- 30 37. A solid shaped article according to claim 36, being a tablet obtained by compressing the said granule population.